



RC.133210 Veepee Industrial Avenue, Km 38, Lagos / Abeokuta Expressway, Sango Ota, Ogun State, Nigeria.
Tel: (+234)-7083179222,(+234)-9095634824,(+234)-9083364874
E-mail: amit@olympicinks.com.ng, milind@olympicinks.com.ng, sales@olympicinks.com.ng
Postal Address: P.O. Box 71121, Victoria Island, Lagos. Nigeria

Technical data sheet

OLEX EXTRUSION LAMINATION INKS

Description

Solvent based Toluene & Ketone free Ink system suitable for printing on Treated Bopp Substrate used for Extrusion Lamination Jobs.

Application

For Food Packaging industries

Print Process

Gravure

Print Substrate

Treated BOPP Substrate

Key Product Feature

Excellent printability and high color strength suitable for High-speed Machines

Excellent adhesion. Low solvent retention.

Good Lamination Bond Strength

Ink Application Details

Thinner ~ Toluene : Ethyl Acetate : MEK (60:20:20)

Retarder ~ MIBK

Running viscosity ~ 16-18 sec (by B4 cup@30°C)

DIRECTORS: S.A. HATHIRAMANI (INDIAN), V.S. HATHIRAMANI (BRITISH)



RC.133210 Veepee Industrial Avenue, Km 38, Lagos / Abeokuta Expressway, Sango Ota, Ogun State, Nigeria.
 Tel: (+234)-7083179222,(+234)-9095634824,(+234)-9083364874
 E-mail: amit@olympicinks.com.ng, milind@olympicinks.com.ng, sales@olympicinks.com.ng
 Postal Address: P.O. Box 71121, Victoria Island, Lagos. Nigeria

SPECIFICATION OLEX INKS

SR. No.	Product Description	INK VISCOSITY (By B4 Ford CUP @ 30°)	SOLID CONTENT	SOLVENT SYSTEM	ARSR PROPERTY	LIGHT FASTNESS VALUE
1	WHITE	35±5 Sec	44±2	TOLUENE : ETHYL ACETATE : MEK	√	7-8
2	YELLOW 13	35±5 Sec	27±2	TOLUENE : ETHYL ACETATE : MEK	√	5
3	MAGENTA 57.1	35± 5 Sec	25±2	TOLUENE : ETHYL ACETATE : MEK	X	2-3
4	CYAN	35±5 Sec	25±2	TOLUENE : ETHYL ACETATE : MEK	√	6-7
5	BLACK	35±5 Sec	26±2	TOLUENE : ETHYL ACETATE : MEK	√	7-8
6	WARM RED 53.1	35±5 Sec	26±2	TOLUENE : ETHYL ACETATE : MEK	X	2-3
7	ORANGE 13	35±5 Sec	25±2	TOLUENE : ETHYL ACETATE : MEK	√	3-4
8	VIOLET 3	35±5 Sec	25±2	TOLUENE : ETHYL ACETATE : MEK	X	3-4
9	GREEN 7	30±5 Sec	25±2	TOLUENE : ETHYL ACETATE : MEK	√	6-7
10	ARSR MAGENTA 146	40±5 Sec	25±2	TOLUENE : ETHYL ACETATE : MEK	√	5-6
11	ARSR RED 8	55±5 Sec	25±2	TOLUENE : ETHYL ACETATE : MEK	√	5

DIRECTORS: S.A. HATHIRAMANI (INDIAN), V.S. HATHIRAMANI (BRITISH)



RC.133210 Veepee Industrial Avenue, Km 38, Lagos / Abeokuta Expressway, Sango Ota, Ogun State, Nigeria.

Tel: (+234)-7083179222, (+234)-9095634824, (+234)-9083364874

E-mail: amit@olympicinks.com.ng, milind@olympicinks.com.ng, sales@olympicinks.com.ng

Postal Address: P.O. Box 71121, Victoria Island, Lagos. Nigeria

12	ARSR VIOLET 23	55±5 Sec	25±2	TOLUENE : ETHYL ACETATE : MEK	√	5-6
13	L/F ORANGE 34	55±5 Sec	25±2	TOLUENE : ETHYL ACETATE : MEK	√	5
14	L/F GREENER YELLOW 17	50±5 Sec	27±2	TOLUENE : ETHYL ACETATE : MEK	√	5-6
15	L/F MAGENTA 48.2	35±5 Sec	25±2	TOLUENE : ETHYL ACETATE : MEK	X	5
16	REDUCING MEDIUM	20±5 Sec	13±2	TOLUENE : ETHYL ACETATE : MEK	√	8

DIRECTORS: S.A. HATHIRAMANI (INDIAN), V.S. HATHIRAMANI (BRITISH)